

400DFP **DRY FALL** MODIFIED COPOLYMER PRIMER

Selection & Specification Data

Product Name Mascoat 400DFP

Product No. M-400DFP

Description Mascoat 400DFP is a 1-part hi-temp dryfall

silicone copolymer primer designed for heated substrates up to 400°F (200°C). The onepart coating's dryfall properties allow it to dry to a powder within 10-20 feet from point of application, allowing it to safely be used in areas where overspray damage to nearby cars and equipment would be a concern. It offers maximum adhesion and corrosion protection even in limited surface preparation areas and does not require a heat cure. Engineered specifically for heavy industrial equipment, M-400DFP may be used on any service area ranging from ambient to 400°F (200°C) for

premium corrosion protection.

◆ Excellent corrosion protection **Features**

♦ Good chemical resistance

Excellent flexibility

Unlimited recoat window

◆ Excellent edge protection

Single coat capability

Outstanding wetting & adhesion properties

VOC Compliant

Light Yellow Color

Flat **Finish**

Single-component Components

>70°F/21°C: Mascoat Reducer 1-400 Reducer

<70°F/21°C: Mascoat Reducer 2-400

Volume Solids Content

43%

Single package Mix Ratio WFT per Coat 5–7 mils (127–178 μ) **DFT per Coat** 2-3 mils (51-76 µ) 345 ft²/gallon @ 2 mils **Theoretical Dry** (8.5 m²/liter @ 51 μ)

Coat Coverage

VOC Content

Unthinned

3.7 lbs/gallon (448 gram/liter)

Reducer 1-400 Reducer 2-400

Limitations Applications should not exceed 400°F

(200°C).

Substrates & Surface Protection

All surfaces should be clean, dry and free of all foreign contaminants. An SSPC-SP1 Solvent Cleaning is recommended before blasting or other cleaning method

Carbon Steel:

Best: An SSPC-SP6 Commercial Blast will provide good results in most situations.

Good: A SSPC-SP3 Power Tool Cleaning, SSPC-SP2 Hand Tool Cleaning, or waterjetting per SSPC-SP 12 to WJ-4 will provide good results.

Galvanized Steel: Contact a Mascoat representative, as recommendation will vary depending on substrate and exposure condition

Application Equipment

Listed below are the general equipment guidelines for the application of this product. It is designed for spray application.

Conventional

DeVilbiss MBC-510 Sprayer

Fluid Tip Ε 704 Air Cap **Atomizing** 60 psi

Pressure

Pot Pressure 20 psi 1/2" Hose

Airless

Graco 205-591 **Sprayer Pump** 30:1/45:1/60:1 Tip Range 3.011-4.013 **Pump Pressure** 1,800 psi ± 25 psi

3/8" ID Hose

Brush/Roller Touch-up Only

Application Conditions

	<u>Material</u>	<u>Surface</u>	<u>Ambient</u>
Minimum	50°F (10°C)	40°F (4.5°C)	45°F (7°C)
Maximum	90°F (32°C)	120°F (49°C)	N/A

Dry-Fall Application Instructions: To ensure dryfall effect, do not apply in temperatures below 45°F (7°C), on surfaces below 40°F (4.5°C), or humidity above 85% Rh. When humidity is above 50%, take caution to observe the dry-fall range as it may extend slightly past the 20' (6 m) mark, up to 50' (15 m) depending on other weather variables. Make sure the equipment being used will give accurate psi readings so the pressure from the pump can be maintained at 1800 psi allowing a maximum +/- 25 psi for surges. Do not apply in temperatures that are 5°F (2.75°C) or less from the dew point.

Resistance Data

Exposure	Immersion	Splash/Spillage	Fumes
Acidic	Not recommended	Good	Good
Alkaline	Not recommended	Good	Good
Solvents	Not recommended	Good	Good
Salt water	Not recommended	Excellent	Excellent
Water	Not recommended	Excellent	Excellent

Mixing & Reducing

Mixing Mascoat 400DFP needs to be thoroughly

mixed using mechanical agitation. It is ready to spray after proper mixing and reduction

Pot Life N/A

Reduction Reduction is required to achieve the dry-fall

effect. Reduce by 15% - 20% with Mascoat Reducer 1-400 in ambient temperatures above 70°F (21°C) or Mascoat Reducer 2-400 in ambient temperatures below 70°F (21°C).

If "fingering" occurs during the spray application, increase the amount of thinner. This will decrease the viscosity of the coating.

DO NOT increase pump pressure.

Packaging, Handling, & Storage

Packaging 1 gallon (3.785 L) & 5 gallon pails (18.93 L)

Weight 1 gallon – 14 lbs (6.35 kg) 5 gallon – 70 lbs (31.75 kg)

Storage Temp 20°F–110°F (-7–43°C)

Flash Point -8°F (-22°C)

(Lowest Flashing Component)

Cleanup & Safety

Cleanup With Reducer 1-400 or Reducer 2-400

Safety

For minimum protection, Mascoat recommends a half mask respirator with organic vapor cartridge. In confined spaces, a fresh airline respirator may

spray application method.

Ventilation Recommended for constricted areas.

Clothing Safety clothing, gloves & barrier creams are

recommended.

Skin Contact If product comes into contact with skin, wash

thoroughly with lukewarm water or diluted Boric Acid, and obtain immediate medical attention.

be used. Eye protection recommended due to

Caution This product contains FLAMMABLE materials.

Keep away from sparks and open flames. Observe

NO SMOKING regulations.

Observe low flash regulation.

All electrical equipment and installations should conform to NEC regulations. In areas where explosion hazards exist, workers should be required to use nonferrous tools, and to wear

conductive, non sparking shoes.

Dry & Cure Times

The following minimum times are based on recommended thickness guidelines and adequate air ventilation. Higher thickness and reduced air circulation increase drying times.

To Touch	10 minute s	
Tack Free	30-60 minutes	
To Topcoat	2-3 hours	
To Handle	2-3 hours	
Put in Service	12 hours	

Mascoat 400DFP has an infinite recoat window, but surface must be free of oil, grease, and debris. An SSPC-SP1 Solvent Cleaning is recommended prior to recoat if a significant period of time has passed since previous coat..